



TECHNICAL DATASHEET

Rephalt 0/4

Description

Reactive hardening, cold processable asphalt mix, free of solvents according to RVS 08.97.01.

Technical characteristics

<u>Characteristics</u>	<u>Test results</u>	<u>Unit</u>	<u>Test in accordance with</u>
Binder content	7 - 8	M%	ÖN EN 12697-1
VOC	0	M%	ÖN EN 14039
Biogenic raw material content	20 - 50	M%	ONR CEN/TS 16640
Stone material			EN13043
Void content	< 9	Vol.-%	ÖN EN 12697-8
Grain loss at -20°C	< 35	M%	ÖN EN 12697-17
ITSR: Splitting tensile strength after water storage at 25°C	> 80	%	ÖN EN 12697-12
ITSw: Remaining splitting tensile strength after water storage at 25°C	0,2 – 0,5	N/mm ²	ÖN EN 12697-12
Marshall stability after 72 h at 60 ° C in the water bath	> 4	kN	ÖN EN 12697-34

Version 3.0

Vialit Asphalt Gesellschaft m.b.H. & Co.KG, A-5280 Braunau/Inn
Josef-Reiter-Straße 78, Tel. 07722/62977-0, Fax 07722/65758
office@vialit.at www.vialit.com www.rephalt.com